

PRELIMINARY TDS COOLMAG SA 20

THERMALLY CONDUCTIVE COMPOUND

DESCRIPTION

COOLMAG SA 20 is a thermally conductive composite PDMS-based elastomeric compound of encapsulant two-component system, designed for Power Electronics in Automotive, especially in Electrified Vehicles with a quadruple functionality:

1. Heat Transfer, reduction of hot spots and minimising average temperature of systems.
2. Electric Isolation.
3. Mechanical protection.
4. Flame and fire protection (Retardant and Extinction).

FEATURES/BENEFITS

Low stress: performs low shrinkage and reduce stress on components as it cures.

Durable: it will not depolymerize when heated in confined spaces.

Environmentally Resistant: Excellent thermal shock resistance.

Flame retardant: COOLMAG SA 20 provides excellent flame retardancy; UL 94 V-O.

APPLICATIONS

Mixing process

Do not dispose of the liquid from above because of the content of essential ingredients for the proper performance of the product. Thoroughly mix each component individually until a viscous paste appearance is obtained. Verify that the solid has been fully incorporated. Vibrating and degassing recommended.

Mix COOLMAG SA 20 resin component A with COOLMAG SA 20 hardener component B at a 1:1 ratio in weight or volume. For high volume production, may be used an automatic meter/mix/dispense equipment.

For high voltage and other critical applications, vacuuming mixing systems may be appropriate: air may be introduced into the encapsulant system either during mixing or when catalysing the mixture changing the electrical and thermo-conductive properties of the product. Thermal conductivity and electric isolation are best when air bubbles and voids are minimized.

Speed Mixers, centrifugal mixers or vibration mixers are recommended.

Applying

Apply COOLMAG SA 20 using hand automatic meter/mix/dispense equipment on a clean surface and without cure inhibiting ingredients, such as amines, sulphur or tin salts.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for applications or the results to be obtained and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end-product performance are the responsibility of the user. COOLMAG THERMO CONDUCTIVE, S.L. shall not be liable for, and the customer assumes all risk and liability of any use or handling of any material beyond COOLMAG THERMO CONDUCTIVE, S.L.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NO LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OFR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

If bonding surface is in question, perform a test with a patch of COOLMAG SA 20, setting for the normal curing time.

Curing

For the proper curing process of the COOLMAG SA 20, after the application needs to be allowed **at room temperature (25°C, 24h) or 40min at 90°C**. Conditions of curing could be longer depending on the volume/quantity, for larger volume/quantity it will require more time. For more specific information, consult with Coolmag Thermo Conductive S.L.

TYPICAL PROPERTIES*

	COOLMAG SA 20 Resin	COOLMAG SA 20 Hardener	COOLMAG SA 20 mixed
Appearance	White	White	White
Viscosity, Brookfield 10 rpm, D94 (cps@ 25°C)	5,000-8,000	5,000-8,000	
Ratio	1	1	
Pot Life (min, 25°C)			20-35
Density, g/cm³	2.6 ±0.2	2.6 ±0.2	2.6 ±0.2

* Data is typical and not to be used for specification purposes.

TYPICAL CURED PROPERTIES**

Thermal Conductivity, W/mk (Hot Disc Transient Method)	1.9-2.1
Dielectric Strength, kV (thickness 2 mm)	>5
Dielectric dissipation factor, tan d (IEC 62631-2-1:2018)	0.2792@50Hz
	0.0520@1kHz
	0.0130@1MHz
Dielectric constant, ϵ_r, (IEC 62631-2-1:2018)	6.19@50Hz
	5.46@1kHz
	4.71@1MHz
Hardness (Shore A, UNE-ISO 7619-1:2011)	30-45
Outgas TEST (ASTM E595)	TBD
Coefficient of linear thermal expansion (ISO 11359-2:2021) ppm/K	121.1 ppm/K (Evaluation area: 23-100; test direction: lengthwise)

**Data is typical and not to be used for specification purposes.

Cure schedule of 40 minutes at 90°C. For the linear thermal expansion measurement, the sample was cured at room temperature.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for applications or the results to be obtained and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end-product performance are the responsibility of the user. COOLMAG THERMO CONDUCTIVE, S.L. shall not be liable for, and the customer assumes all risk and liability of any use or handling of any material beyond COOLMAG THERMO CONDUCTIVE, S.L.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NO LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OFR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

REGULATIONS

REACH (Regulation (EC) 1907/2006).

RoHS II (Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU).

PACKAGING, STORAGE AND SHELF-LIFE

COOLMAG SA 20 is packed in:

- 5 kg (5,5 liters, plastic pail, 215mm diameter x 195mm height)
- 20 Kg (16 liters, metallic drum, 29.2 diameter x 27.3 height)

Before using COOLMAG SA 20, please refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/professional use only. Must be applied by trained personnel only. Do not use in household applications nor for consumer use.

The shelf-life of each component is 6 months from date of manufacture, in the unopened original container at 25°C.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for applications or the results to be obtained and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end-product performance are the responsibility of the user. COOLMAG THERMO CONDUCTIVE, S.L. shall not be liable for, and the customer assumes all risk and liability of any use or handling of any material beyond COOLMAG THERMO CONDUCTIVE, S.L.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OFR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.